



# Decolastic 250

## Hybrid Acrylic Elastomeric Textured Finish

### TECHNICAL DATA

REPORT	TEST METHOD	TEST CRITERIA	TEST RESULTS
<b>Flexibility</b>	ASTM D-522	1/8" mandrel bend	Pass
<b>Water Vapor Transmission</b>	ASTM E-96	ICC Vapor Permeability	Pass
<b>Accelerated Weathering</b>	ASTM G-154	2000 hours	No deleterious effects
<b>Surface Burning</b>	ASTM E-84	≤ 25 Flame Spread ≤ 450 Smoke Developed	Pass
<b>Freeze-thaw Resistance</b>	ASTM 2485	60 cycles	Pass; No deleterious effects
<b>Adhesion (psi)</b>	ASTM D-4541	28 days	> 105 to concrete > 80 to stucco

*Decolastic 250 Hybrid Elastomeric, Acrylic Textured Finishes are water based textured coatings formulated to provide a tough, durable, flexible, and breathable coating. Used as decorative wall finish over concrete, masonry, stucco, and EIFS.*

*Available in the following textures*

#### Coverage

Ispica (Freestyle): Varies with technique.

Genova (Fine Sand): 130 -145 ft<sup>2</sup> (12.1-13.5 m<sup>2</sup>) per pail.

Trieste (Medium Sand):  
115 - 130 ft<sup>2</sup> (10.7-12.1 m<sup>2</sup>) per pail.

San Remo (Coarse Sand):  
85 - 100 ft<sup>2</sup> (7.9-9.3 m<sup>2</sup>) per pail.

Taormina (Fine Swirl): 160 -180 ft<sup>2</sup> (14.8-16.7 m<sup>2</sup>) per pail.

Graffiato (Medium Swirl): 130 - 145 ft<sup>2</sup> (12.1-13.5m<sup>2</sup>) per pail.

*Coverages may vary depending on application technique and surface conditions.*

#### Packaging

5 gal pail (19L) 68.5 lbs / 31 kg per pail

#### Shelf Life

24 months, if properly sealed and stored.

#### Storage

Store off the ground in a cool/dry area. Protect from extreme heat [90°F (32°C)], moisture and direct sunlight.

### FEATURES BENEFITS

<b>Elastomeric</b>	Bridges hairline cracks
<b>Acrylic-Based</b>	Excellent adhesion
<b>Ready-Mixed</b>	Ready to use on site; no additional additives needed
<b>Water-Based</b>	Safe, non-toxic; cleans up with water

### SURFACE PREPARATION

**Concrete and masonry surfaces:** Surfaces must be clean, dry, and free of frost, damage, releasing agents, including dirt, efflorescence, form oil and other foreign matter. Loose or damaged material must be removed by water blasting, sandblasting or mechanical wire brushing and repaired. Avoid application over irregular surfaces. Resurface, patch or level surfaces to required tolerance and smoothness with appropriate Decoplast leveling materials.

**Decoplast recommends priming cementitious substrates using Decoplast primer prior to application of finish:**

For color uniformity, maximum finish coverage, and neutralizing high pH (highly alkaline) surfaces.

### MIXING

Mix with a clean, rust-free electric drill and paddle to a uniform consistency. A small amount of clean water may be added to aid workability. Limit addition of water to amount needed to achieve the finish texture. Additives are not permitted. Close container when not in use. Clean tools with water immediately after use.



## Decolastic 250 Hybrid Acrylic Elastomeric Textured Finish

### APPLICATION

Apply only to sound and clean, dry, properly prepared surfaces.

**Trowel:** Apply Decolastic 250 Textured Finish with a clean stainless steel trowel to a rough thickness slightly more than the largest aggregate size. Apply the finish keeping thickness uniform. Maintain a wet edge on Decolastic 250 Textured Finish by applying and texturing continually over the wall surface. Work Decolastic 250 Textured Finish to corners, joints or other natural breaks. Do not allow material to set up within an uninterrupted wall area. Achieve final texture by floating with the appropriate trowel.

**Spray:** Decolastic 250 Textured Finishes can be applied with a gravity-feed sprayer, texture spray pump machine, or other appropriate equipment. To ensure full coverage of the surface, apply in an even coat.

**IMPORTANT:** ALWAYS check color for proper match.

Apply coating continuously, maintain a wet edge to eliminate cold joints. Work Decolastic 250 Textured Finish to corners, joints or other natural breaks. Avoid application in direct sunlight. Protect installed product from rain, freezing, and continuous high humidity until completely dry.

#### Curing/Drying

Decolastic 250 Textured Finishes dry within 24 –72 hours under normal conditions [70°F (21° C), 50% RH]. Drying time varies with temperature, humidity and surface conditions.

#### Clean Up

Clean tools and equipment with water immediately after use. Remove dried material from tools and equipment mechanically.

### LIMITATIONS

Use Decolastic 250 Textured Finishes only when surface and ambient temperatures are above 45°F (4°C) and below 100°F (38°C) during application and drying period.

Store Decoplast materials in a cool, dry place.

Sloped surfaces: Refer to Decoplast details.

Decolastic 250 Textured Finishes should not be used on weather-exposed horizontal or below grade surfaces or where immersion in water may occur.

Do not apply Decolastic 250 Textured Finish to frozen surfaces.

### HEALTH AND SAFETY

#### Health Precaution

Decolastic 250 Textured Finishes are water-based. As with any chemical construction product, exercise care when handling.

#### WARNING!

Causes eye and skin irritation.

#### Safety Precaution

Wash hands thoroughly after handling. Wear protective gloves/protective clothing/eye protection/face protection.

#### First Aid:

**EYE CONTACT:** Immediately flush eyes with plenty of water for at least 15 to 20 minutes. Ensure adequate flushing of the eyes by separating the eye lids with fingers. Get immediate medical attention.

**SKIN CONTACT:** Immediately wash skin with plenty of soap and water for at least 15 to 20 minutes, while removing contaminated clothing and shoes. Get medical attention if irritation develops or persists.

**INHALATION:** If inhaled, remove to fresh air. If not breathing give artificial respiration or give oxygen by trained personnel. Seek medical attention immediately.

**INGESTION:** If swallowed, do NOT induce vomiting. Call a physician or a poison control center immediately. Never give anything by mouth to an unconscious person.

#### Spills

Contain and clean with appropriate absorbent materials.

#### Disposal

Dispose of in accordance with local, state or federal regulations.

#### Warning

KEEP CONTAINER CLOSED WHEN NOT IN USE. KEEP OUT OF THE REACH OF CHILDREN. NOT FOR INTERNAL CONSUMPTION. FOR INDUSTRIAL USE ONLY. Consult the Safety Data Sheet (SDS) for further health and safety information.

#### LIMITED WARRANTY

This product is subject to a written limited warranty. Refer to Decoplast Specifications for more complete information on proper use and handling of this product.



697 Oakwood Avenue, West Hartford, CT 06110  
voice: 860.761.2830 fax: 860.761.2831  
www.decoplast.com

This product is intended for use by qualified professional contractors. All information conforms to the standard detail recommendations and specifications for the installation of Decoplast systems and is presented in good faith as of the date of publication of this document. GREENMAKER INDUSTRIES ASSUMES NO LIABILITY, EXPRESSED OR IMPLIED, AS TO THE WORKMANSHIP, ENGINEERING OR ARCHITECTURE OF ANY PROJECT. For more information regarding this product or additional Decoplast products, please contact a Decoplast Representative at (860) 761-2830 or visit our website [www.Decoplast.com](http://www.Decoplast.com).